

GO
DOP 71

MW - EN 14064

RI
SE
Research Institutes
of Sweden



TERMOLAN
ISOLAMENTOS TERMO-ACÚSTICOS, S.A.

DEFINITION:

Rolled loose stone wool, consisting of fibers with low binder content.

APPLICATIONS:

Multiple applications such as thermal insulation on uneven surfaces, especially in places with difficult access: ovens, exhausts, cisterns, cryogenics, etc.

BENEFITS:


- Easy and quick application;
- Multiple applications;
- Ideal for points of difficult accessibility or irregular shapes;
- Good insulation performance;
- Fire safety;
- Non-corrosive and chemically neutral;
- Good water behaviour;
- Inert product respecting the environment (CFC and HCFC free).

PRESENTATION:

Rolls.

PACKAGING:

Rolls packed in retractile plastic.
Geometry (AxBxH):



PHYSICAL PROPERTIES OF MATERIALS

NOMINAL DENSITY

Depends and is determined by the application

TEMPERATURE

ISO 528

SERVICE: **-250 °C a 750 °C**

VITRIFICATION: **1150 °C**

SPECIFIC HEAT

c = 0.84 kJ/kg.°C

THERMAL CONDUCTIVITY, λ

EN 12667

MEDIUM TEMPERATURE (°C)	10	50	100	150	200	250	300	350	400
λ (W/m.K)	0.040	0.040	0.045	0.056	0.066	0.079	0.095	0.112	0.128
λ (kcal/h.m.K)	0.034	0.034	0.039	0.048	0.057	0.068	0.082	0.096	0.110

Note: For cryogenic applications the values of λ are determined for each case.

FIRE REACTION

EN 13501-1
ISO 1182

Incombustible

WATER ABSORPTION

Indeterminate

WATER VAPOUR DIFFUSION FACTOR

EN 12086

$\mu = 1.30$

BIOLOGICAL BEHAVIOR

Inorganic, the material does not constitute an environment favorable to the proliferation of fungus, parasites or other micro-organisms.

CHEMICAL BEHAVIOR

The stone wool fibre have a composition that is similar to that resulting from the original rocks They are chemically neutral, with a pH of 7, and do not react to chemical agents.



TERMOLAN

www.termolan.pt/en | www.rocterm.com | termolan@termolan.pt